

Eurofins Product Testing Services Ltd
Charter House
WA14 1HF Altrincham
UNITED KINGDOM

Eurofins Product Testing A/S
Smedeskovvej 38
DK-8464 Galten
Denmark

Tel. +45 70 22 42 76
Fax +45 70 22 42 75
eurofins@eurofins.dk
www.eurofins.com/product-emissions

Date
09 October 2014

Our ref.
392-2014-00196503

Test Report – ISO 11890-2 / ASTM D6886

Sample material

Sample identification	Erasable Whiteboard Finish; Part A + Part B, ready-to-use
Product data	Density: 1.36 g/ml (Calculated from information from costumer)
Date received	09/09/2014
Analytical period	18/09/2014 – 09/10/2014

Methods applied

Method	Principle	Parameter	Reporting limit	Uncertainty (U _m)
EU Directive 42/2004/EC ISO 11890-2 (2013) ASTM D6886-12	GC/MS and GC/FID	Content of volatile organic compounds (VOC) in paints and varnishes	1 g/l	20 %

VOC includes all VOC with a boiling point < 250 °C.

Analytical results

392-2014-00196503	CAS	Content, g/l
Sum of unidentified *	-	42
Total VOC	-	42

Eurofins Product Testing A/S



Nikolaj Røjkjær Andersen
Analytical Chemist

*)Not accredited

The expanded uncertainty U_m equals 2 x RSD%

The test results relate only to the items tested.

The report shall not be reproduced except in full without the written approval of the testing laboratory.